

Außenstelle Erwitte • Auf den Thränen 2 • 59597 Erwitte • Telefon (0 29 43) 8 97-0 • Telefax (0 29 43) 8 97-33 • E-mail: erwitte@mpanrw.de

Report of the classification of the reaction to fire behaviour

No. 230009713-4 issued 12 April 2016

English version

Sponsor: Neukölln Spezialpapier GmbH

Wöhrmannkehre 2

12359 Berlin

Order: Reaction to fire classification according to DIN EN 13501-1

Date of order: 10 March 2016

Name of the classified building product:

Wallpaper "TV 90-150"

This report determines the classification of the above-mentioned building product in accordance with the method specified in DIN EN 13501-1



1 Description of the building product

Wallpaper "TV 90-150":

Thickness:

160 μm to 285 μm

Weight per unit area:

90 g/m² to 154 g/m²

Colour:

white

The wallpaper fleece consists of cellulose, synthetic fibre and acrylate binder.

2 Test report and test results which form the basis of the classification

2.1 Test reports

Name of the laboratory	Sponsor	Number of the test report	Test method
MPA NRW	Neukölln Spezialpapier GmbH Wöhrmannkehre 2 12359 Berlin	230009713-1 of 04.11.2014 and 230010466-1 of 12.04.2016	DIN EN 13823
MPA NRW	Neukölln Spezialpapier GmbH Wöhrmannkehre 2 12359 Berlin	230009713-2 of 04.11.2014 and 230010466-2 of 12.04.2016	DIN EN ISO 11925-2

2.2 Test results

Test method	Number of tests	Parameter	Test results
	4	FIGRA _{0,2 MJ} (W/s) FIGRA _{0,4 MJ} (W/s) THR _{600s} (MJ) LFS	120 75 1.3
DIN EN 13823		SMOGRA (m²/s²) TSP _{600s} (m²)	< edge 1 47
		Duration of production of flaming droplets / particles (s)	0
DIN EN ISO 11925-2 Flame impingement: 30 s	24	F _s (mm) Flaming droplets / particles	<= 150 no



3 Classification and direct field of application

3.1 Reference

The classification was carried out in accordance with clauses 11 and 14.1 of the standard DIN EN 13501-1: 2010.

3.2 Classification

The classification assigned to the material with regard to its reaction to fire is:

The additional classification with regard to smoke production is: \$1

The additional classification with regard to flaming droplets / particles is:

This results in the following reaction to fire classification of the material:

Reaction to fire	Smoke production	Flaming droplets / particles		
В	s1	d0	i.e.	B-s1,d0

3.3 Field of application of the product

The classification is solely valid for the building product described in clause 1 when it is glued like in practice with "Methylan Direkt" or "Methylan Spezial" onto gypsum plasterboards according to DIN EN 13238 (table 1) or onto substrates which are classified as class A1 or A2 according to DIN EN 13501-1 and which have a minimum raw density of 525 kg/m³ and a minimum thickness of 12 mm.

4 Restrictions

This classification report does not replace any type approval or certification of the product.

This classification report written in English language is issued additionally to the report written in German language with the same report number. In case of doubt the German version is solely valid.

Erwitte, 12 April 2016

On behalf

Head of the testing body

p.p.

(Dipl.-Ing. Kühnen)

Date of issue of this English version: 17 May 2016